



HEADSTONE FOUNDATION NOTES

- A.** CLASS C, NONREINFORCED CONCRETE SHALL BE USED.
- B.** THE DEPTH OF CONCRETE TO BE NO LESS THAN 24". THE LENGTH AND WIDTH OF THE FOUNDATION ARE DETERMINED BY ADDING 2" TO THE HEADSTONE BASE DIMENSIONS.
- C.** THE TOP 4" (MINIMUM) SHALL BE SQUARED, FORMED AND LEVELED.
- D.** THE SUBGRADE SHALL BE LEVELED AND COMPACTED TO PREVENT ROTATION OF THE FOUNDATION.
- E.** ONCE POURED, EXCESS CONCRETE IS TO BE STRUCK OFF THE TOP. A SMOOTH FINISH SHALL BE PROVIDED.